



SPECIFICATIONS

MEARLCRETE[®] 40 Low Density Cellular Concrete (LDCC)

SCOPE OF WORK: The certified MEARLCRETE[®] 40 LDCC applicator shall furnish labor, materials, equipment and supervision for the installation of MEARLCRETE 40 LDCC in accordance with the drawings and specifications.

MATERIALS: MEARLCRETE 40 LIQUID FOAM CONCENTRATES shall be supplied by CELLULAR CONCRETE SOLUTIONS, Allentown, PA. MEARLCRETE 40 LIQUID FOAM CONCENTRATES shall comply with the standard specifications of ASTM C 869 when tested in accordance with ASTM C 796.

Portland cement shall comply with ASTM C 150, Type I, II or III. Mixing water shall be potable and free from deleterious amounts of acids, alkali, salts, oils and organic materials which would adversely affect the setting or strength of the MEARLCRETE 40 LDCC. Admixtures for reducing water, accelerating set, etc., may be used when specifically approved by CELLULAR CONCRETE SOLUTIONS and in accordance with its recommendations. Other additives such as fly ash may be used when specifically approved by CELLULAR CONCRETE SOLUTIONS.

MIX DESIGN: Mix design shall be in accordance CELLULAR CONCRETE SOLUTIONS recommendations for a cast density at point of placement of _____pcf _____pcf with a compressive strength of _____psi at 28 days.

MIXING AND PLACING: MEARLCRETE 40 LDCC shall be job site batched, mixed and placed with equipment (foam generator, mixer and pump) approved by CELLULAR CONCRETE SOLUTIONS

TESTING: Four (4) test specimens shall be taken at the point of placement for each 100 cubic yards of MEARLCRETE 40 LDCC. Specimens shall be prepared, handled, cured and tested for compressive strength in accordance with ASTM C 495.

SPECIAL CONSIDERATIONS: Contact CELLULAR CONCRETE SOLUTIONS for design assistance, application and placement recommendations.

SP204-0210